

Experimental investigation of ultra-high performance concrete slabs under contact explosions

Jun Li^{1, 2,*}, Chengqing Wu^{1, 2}, Hong Hao³, Zhongqi Wang⁴, Yu Su^{1, 2}

¹TCU-UA (Tianjin Chengjian University-University of Adelaide) Joint Research Centre on
Disaster Prevention and Mitigation

²School of Civil, Environmental and Mining Engineering, the University of Adelaide, SA, Australia 5005

³School of Civil and Mechanical Engineering, Curtin University, WA, Australia 6845

⁴The State Key Laboratory of Explosion Science and Technology, Beijing Institute of Technology, China

11 Abstract

Unlike ductile behaviour under static loads, a reinforced concrete structure can respond in a brittle manner with highly localized damage like concrete spalling, cratering and reinforcement rupturing under close-in or contact explosions. High speed fragmentation resulting from concrete spall may cause severe casualties and injuries. It is therefore important to have a better understanding of the concrete spall phenomena and fragments distribution. In the present study, contact explosion tests were carried out on concrete slabs to observe the concrete crater and spall damage. Seven slabs including two control specimens made of normal strength concrete (NRC) and five ultra-high performance concrete (UHPC) slabs are tested. The superior blast resistance capacity of UHPC slabs is verified through comparison against NRC slabs. The influence of longitudinal reinforcement spacing and slab depth on the spall resistance of UHPC slabs is investigated. Predictions through available empirical methods are made and compared

*Corresponding author. Email: j.li@adelaide.edu.au; Telephone: (08) 8313 1231

23 with the test observations. The accuracy of these empirical methods is discussed. All fragments
24 resulting from the contact blast tests are collected and analysed through sieve analysis. It is
25 found that Weibull distribution can be used to model the fragments size distribution of NRC
26 slabs while Log-normal distribution better models the fragments size distribution of UHPC
27 slabs.

28

29

30

31

32 **1. Introduction**

33 In modern society, reinforced concrete (RC) is one of the most commonly used construction
34 materials. During the service life of a RC structure, accidental or intentional explosion is a
35 threat with relatively low probability but disastrous consequences. Blast loads with large
36 amplitude and short duration impart tremendous amount of energy to the structure and excite
37 global and local response associated with damages including immediate effects like failure of
38 structural members and consecutive hazards like structural progressive collapse. This threat
39 has drawn renewed interests since the rising of terrorism activities in recent decades.

40 Under blast loading conditions, structures and their components can fail in multiple ways. For
41 structural load-carrying members like columns and slabs, if damage is unavoidable, flexural
42 damage is always the desired damage mode as such damage is most ductile and can absorb a
43 largest amount of blast energy. However, in most blasting scenarios, brittle damage modes like
44 shear damage or combined flexural and shear damage are commonly observed [1-3]. It is
45 assumed that a large loading with short duration is more likely to cause a shear failure mode

46 while a relatively small amplitude load with longer duration will result in flexural failure; this
47 phenomenon is well understood, and some researches have been carried out to define the
48 structural and blast loading conditions for causing the respective damage modes [4, 5]. For
49 high rise buildings in modern city, failure of one or several key load-carrying members may
50 trigger the disproportionate progressive collapse with catastrophic casualties and property loss
51 [6, 7]. The failure mechanism behind the progressive collapse phenomena has been under an
52 ongoing discussion [8, 9].

53 When an explosion is in close proximity to or in contact with a concrete structure, on the surface
54 facing the detonation, the concrete experiences compression and may fail under high
55 compressive force and generate cratering. When the compressive shock wave propagates in the
56 structure and interacts with the free surface, it will be reflected and converts to a tensile wave.
57 Under this condition, due to the low tensile resistance of concrete, cracks will form if the net
58 stress exceeds concrete dynamic tensile strength. Furthermore, if the trapped impulse is large
59 enough to overcome the resistant forces such as the bond, shear around the periphery of the
60 cracked portion, and the mechanical interlocking, the cracked off parts will displace from the
61 backside of the structure at some velocity [10].

62 Unlike other damage modes like flexural or shear damage, concrete spall damage is usually not
63 considered in conventional protective designs of concrete structures. However, in some
64 extreme cases, localized damage of concrete crushing and spalling can result in complete loss
65 of structural loading capacity which may promote the progressive collapse. Moreover the high-
66 speed debris accompanying the concrete spall could cause unexpected casualties and property
67 loss.

68 Researches on concrete spallation under blast environment have been carried out in the past
69 several decades. Back in the 1970s, Kot et al. [11, 12] proposed theoretical prediction methods

70 for spall damage of concrete wall, however these methods were limited to light and moderate
71 bomb threats and were based on several simplified assumptions which compromised the
72 calculation accuracy. Later in 1980s, a series of concrete spall tests from different sources were
73 summarized by McVay [13], and parameters affecting concrete spall were investigated and
74 these parameters included scaled standoff distance, explosive charge weight, wall thickness,
75 concrete strength, concrete additives and reinforcement spacing. Based on the test results, an
76 empirical approach for determining if and where a stress wave would cause the concrete to
77 crack in tension was derived. In this method, the changes in the stress caused by stress waves
78 travelling at different velocities, wave attenuation, and dispersion were neglected. The only
79 change in the stress wave propagation that was taken into consideration was wave divergence.
80 Recently, Wang et al. [14] carried out close-in explosion tests on square reinforced concrete
81 slabs and spall damage at different severity was observed, and the experimental results were
82 used to verify their numerical model. Based on a large database of empirical slab/wall tests,
83 AFRL-MN-EG-TR-1998-7032 *Concrete Hard Target Spall and Breach Model* [15] details the
84 development of a spall/breaching algorithm for RC slabs and walls.

85 Different from a slab or wall in which only the reflection of the blast induced stress wave from
86 the back surface needs be considered, a stress wave in a column generated from a close-in
87 detonation can be reflected from both the back and side faces which makes it a 3D shock
88 propagation problem. In NCHRP Report 645 [16], test results from eleven concrete columns
89 were compiled and used to evaluate the performance of several design parameters and to
90 determine the capacity and failure limit states of concrete highway bridge columns. Wu et al.
91 [17] carried out contact explosion test on steel-concrete composite column and developed
92 numerical model reproducing the spall damage. Based on extensive parametric studies, they
93 [18] investigated the relationship between residual axial capacity and structural and loading
94 parameters such as material strength, column detail and blast conditions. In a recent study, Li

95 and Hao [10] developed three-dimensional numerical models to predict the concrete column
96 spalling under blast loads. Intensive numerical simulations were carried out to investigate the
97 influences of the column dimensions and reinforcement mesh on concrete spall damage.

98 Recent decades have witnessed an increasing demand of structural protection under explosive
99 loads, and tremendous efforts have been dedicated to the development of new concrete material
100 or concrete retrofitting technology. Riisgaard et al. [19] introduced an efficient method for
101 implementing high fractions of polymer shock reinforcement into a compact reinforced
102 composite, and a significant improved blast resistance was observed. Wu et al. [20] conducted
103 air blast tests on two RC specimens in a blast chamber, it was observed that RC specimen
104 retrofitted with 6 near surface mounted (NSM) carbon fibre reinforced polymer (CFRP) plates
105 on both the top and bottom faces outperformed the conventional reinforced RC specimen.
106 Ohtsu et al. [21] experimentally and analytically investigated the dynamic failure of fibre-
107 reinforced concrete (FRC) slabs, and it was observed that the averaged diameters and the
108 volumes of the spall failure remarkably decreased with the increase in the flexural toughness
109 of FRC concrete. Ohkubo et al. [22] conducted contact-explosion tests on concrete plates
110 reinforced by carbon or aramid fibre sheet, and it was noted that local spall damage had been
111 significantly reduced with fibre sheet reinforcement, and fibre sheets also had prevented
112 concrete plates from fragmentation. Recently Foglar and Kovar [23] plotted their experimental
113 results on these spall and breach prediction curves, and they concluded that the observed spall
114 damages in RC specimens agree with the spall and breach prediction curves according to UFC
115 3-340-02 [24]. However, they also noted the spall and breach prediction curves according to
116 UFC 3-340-02 are not suitable for predicting the spall damage in fibre reinforced concrete.
117 Moreover, the spall damage severity is not clearly defined in UFC guideline. Therefore it can
118 only predict the occurrence of spall damage in the wall slab under a blast load, but cannot
119 quantify the damage levels.

120 Ultra-high performance concrete (UHPC) is a relatively new construction material with higher
121 strength, deformation capacity and toughness. The outstanding mechanical properties of UHPC
122 stems not only from addition of high pozzolanic particles like silica fume but also from the
123 reinforcement of small steel fibres in the concrete matrix. Previous experimental study
124 conducted by Wu et al. [25] confirmed the superior blast resistance of UHPC.

125 In the present study, to further investigate the concrete spall damage, especially the spall
126 phenomena of ultra-high performance concrete, contact explosion tests were carried out on
127 seven slabs. In the seven slabs, two slabs were constructed with conventional concrete and the
128 other five slabs were made of ultra-high performance concrete with different slab depths and
129 longitudinal reinforcement spacing. The spall areas and crater areas are quantitatively analysed
130 and compared. Feasibility of utilizing existing theoretical and empirical methods predicting
131 concrete spallation under blast loads is discussed. Furthermore the fragments from each single
132 test were collected for a sieve analysis, and the results are used for predicting fragments size
133 distribution.

134

135 **2. Contact-explosion tests on concrete plates**

136 **2.1 Explosive charges**

137 TNT explosives with a Heat of Detonation density of 4521 kJ/kg and a material density of 1.65
138 g/cm³ were used in the tests. Two cylindrical charges with a mass of 0.1 kg and 1.0 kg were
139 placed on the top centre of the slabs. Detonator was used to electrically activate the explosive.
140 As shown in Figure 1a, the electrical detonator was bonded together with the TNT through
141 adhesive bandage. The explosive in the detonator is Hexogen (RDX) with TNT equivalence of
142 1.58. One detonator contains 0.4-0.6 g RDX with NEQ (net explosive quantity) less than 1 g
143 TNT per detonator. Comparing with the explosive charge weights used in the current tests (100

144 g and 1000 g TNT), the effects from the detonator is deemed not prominent and can be
145 neglected.

146 Figure 1 illustrates the dimensions of the TNT explosives used in the tests.

147

148 **2.2 Sample preparation**

149 In total seven slabs including two normal strength concrete (NRC) slabs and five micro steel
150 fibre reinforced ultra-high performance concrete (UHPC) slabs were tested. As shown in Figure
151 2, the dimension of slabs is: 2000 mm long, 800 mm wide and 100-150 mm thick. Slabs of
152 different depths were designed to explore the depth influence on the spall damage. One of the
153 five UHPC slabs was reinforced by less longitudinal reinforcement bars in which the rebar
154 number in the compressive and tensile surface decreased from 9 each to 5. This modification
155 was made to investigate the influence of longitudinal reinforcement spacing on slab response.
156 The diameters of the longitudinal reinforcing rebar and stirrup rebar are 12 mm and 8 mm,
157 respectively. Both of these two reinforcements have 360 MPa yielding strength.

158

159 Two control NRC slabs were constructed by concrete with unconfined compressive strength of
160 40 MPa. In UHPC material, micro steel fibres with a length of 15 mm and diameter of 0.12
161 mm were mixed at a volume dosage of 2.5%, the tensile strength of the micro steel fibre is
162 4295 MPa. Ultra-high performance fibre reinforced concrete with uniaxial compressive
163 strength 145 MPa and tensile strength 22 MPa was used to build the UHPC slabs. Material
164 composition of the current UHPC material is given in Table 1. Typical stress-strain relationship
165 obtained from uniaxial compression test and force-displacement relationship obtained from
166 four points bending test are shown in Figure 3.

167 During the sample preparation, strain gauges were attached to the reinforcement bars at
168 different locations in each slab as indicated by red dots in Figure 2. The positions where the
169 strain gauges located were carefully grinded using electrical grinder, and later mopped using
170 liquid acetone. These procedures were carried out to guarantee the contact between the strain
171 gauge and reinforcing bar. Strain gauges were used to record the strain time history and the
172 data obtained can be further used to derive the strain rate experienced by the slabs in each blast
173 scenario.

174

175 **2.3 Experimental setup**

176 As depicted in Figure 4, the slab was firstly placed on the steel rig using a crane, then both ends
177 of the slab were bolt fixed with the angle steel cleats. In the previous study carried out by Beppu
178 et al. [26] and Ohkubo et al. [22], a simply supported boundary was adopted to study the contact
179 explosion resistance of concrete slab reinforced with FRP laminates. It is deemed that contact
180 explosion induces highly localized response and damage which is independent of the boundary
181 condition.

182 **2.4 Test program**

183 In total seven shots were carried out in the current study. In test events 1 and 2, two identical
184 NRC slabs reinforced by 9 Ø 12 mm longitudinal rebars and 11 Ø 8 @ 200 mm stirrup rebars
185 (as shown in Figure 2) were subjected to contact explosions of cylindrical explosives of 0.1 kg
186 and 1 kg, respectively to obtain different level of damages. In blast events 3 and 4, two UHPC
187 slabs with the same reinforcements as the two reference NRC slabs were also subjected to the
188 same blast scenarios in order to compare the blast resistances of NRC slabs with those of UHPC
189 slabs. The influence of the slab depth was investigated in blast events 4-6, in which three UHPC
190 slabs with different thickness but the same reinforcements were subjected to 1 kg TNT contact

explosion. To investigate the reinforcement mesh confinement effect on spalling damage, UHPC-7 slab in blast event 7 was made the same as UHPC-4 but with less number of the longitudinal reinforcements in both the compressive and tensile face, i.e., the number of longitudinal reinforcement bars is reduced to 5 from 9. The slab was also tested with 1.0 kg contact explosion. Comparison was made between UHPC-7 and UHPC-4 to investigate the influence of reinforcement mesh confinement effect on concrete crushing and spalling damages.

The test program is summarized in Table 2.

198

199 **2.4 Results and discussion**

200 NRC-1 is a NRC slab with conventional steel reinforcement. 0.1 kg TNT was placed at the
201 centre of slab surface as shown in Figure 5. After explosion, clear spall damage and concrete
202 crater were observed on the bottom and top surface of the slab. The diameters of the concrete
203 crater and spall were 20 cm and 33 cm, respectively. Neither perforation nor flexural damage
204 was found at the slab mid-span.

205 In blast event 2, normal strength concrete slab NRC-2 was subjected to 1 kg TNT placing also
206 at the centre of slab surface. As can be noticed from Figure 6, severe blast load induced
207 perforation failure in the slab. Fracture happened on the central stirrup reinforcement. It is also
208 noted that significant concrete cracking occurred along the two unsupported directions near the
209 slab boundary. As no obvious slab deformation was observed, these damages were believed
210 also caused owing to stress wave propagation and reflection. Stress wave caused cracks along
211 the two free ends because of the short propagation distance between the explosive and the free
212 boundary, which generated large tensile stresses owing to wave reflection and hence cracking
213 of concrete.

214

215 UHPC-3 was an UHPC slab with the same steel reinforcement as the two NPC slabs. 0.1 kg
216 TNT was placed at the centre of slab surface and detonated. As shown in Figure 7, after
217 explosion, no spall damage was observed on the bottom surface of the slab, and a small concrete
218 crater with a diameter of 9 cm and a depth of 2.7 cm was found on the top surface. Comparing
219 with NRC-1 slab which has the same steel reinforcement and subjected to the same blast load,
220 it is clear that UHPC material has much higher blast resistance capacity.

221 UHPC-4 was tested with a 1 kg TNT detonated at its central surface. The slab was observed
222 with spall and concrete crushing failure. Compared with NRC-2 slab under the same blast load,
223 it was noted that UHPC-4 slab has better blast resistance capacity. The top surface crater
224 diameter and the bottom surface spall diameter were reduced from 46 cm and 82 cm to 23 cm
225 and 45 cm, respectively. Moreover, no side concrete cracking as in NRC-2 was observed, and
226 no reinforcement fracture was observed either. These comparisons clearly demonstrate the
227 better blast loading resistance capacity of UHPC than normal concrete.

228 UHPC-5 was an UHPC slab with a depth of 100 mm. The reinforcements in the slab were kept
229 the same as in the previous slabs. As shown in Figure 9, subjected to 1 kg contact explosion,
230 the slab suffered perforation failure. The stirrup and longitudinal reinforcements at mid span
231 were also fractured. Slight side concrete cracking which was similar to NRC-2 slab under 1 kg
232 TNT was also noticed. Comparing with UHPC-4, the crater diameter and spall diameter both
233 increased, indicating slab depth played a positive role in resisting the contact explosion induced
234 damage, as expected.

235 UHPC-6 was an UHPC slab with an increased depth of 150 mm subjected to 1 kg TNT contact
236 explosion. Similar to the previous two trials, perforation failure was again observed. However
237 the damage severity was reduced. Comparing with UHPC-5, the top surface crater diameter
238 and bottom surface spall diameter dropped from 27 cm and 47 cm to 22 cm and 41 cm,

239 respectively. Only one longitudinal rebar at the bottom side was fractured. No side concrete
240 cracking was observed in this thicker slab.

241 As mentioned above, the UHPC-7 slab was made with less number of reinforcements. It was
242 also subjected to the same 1 kg TNT explosion. After the test, severe perforation failure was
243 observed. Comparing with UHPC-4, the top surface crater diameter and bottom surface spall
244 diameter increased from 23 cm and 45 cm to 25 cm and 48 cm, respectively. Longitudinal
245 reinforcement at mid span experienced fracture failure which was not observed in UHPC-4.
246 Generally speaking, the reinforcement mesh contributed to the resistance against the contact
247 blast loads. However, in this particular case, the crater and spalling damage dimensions only
248 slightly increased even the number of reinforcement bars were almost reduced to half as
249 compared to UHPC-4, indicating the reinforcement confinement effect is not prominent. This
250 observation nonetheless is based on only two types of reinforcement meshes. It is believed that
251 if denser reinforcement mesh was used, its confinement effect on concrete would have been
252 more prominent. More studies are deemed necessary to confirm and possibly quantify the
253 reinforcement confinement effects on concrete materials subjected to blast loadings.

254 As observed from the above tests results, the failure modes of slabs under contact explosion
255 can be classified into three categories, i.e. “crater only”, “crater and spall”, and “perforation”.
256 Table 3 summarizes the test results.

257

258 Figure 12 shows the recorded strain time histories on refinement bars. Locations of the five
259 strain gauges are depicted in Figure 2. It should be noted that no meaningful strain data was
260 successfully recorded in UHPC-3 and UHPC-5 owing to malfunction of the sensor and/or
261 equipment during these two tests. The strain time histories were recorded by resistance strain
262 gauges provided by Jin-Li Sensor Company from China. The effective length of the gauge is 5

263 mm. The strain gauges were placed along the longitudinal direction of the rebars. Testing
264 circuit was quarter-bridge strain gauge circuit with 2 V powering voltage and 100 amplification
265 coefficient. The data was collected by high speed data collecting system TST5205 provided by
266 Chengdu-Test company. The sampling rate was set at 1 million Hertz in all the recordings.

267 Under contact explosion, the intense blast load is highly localized with extremely short duration.
268 During the blast loading phase, the global structural response (shear and bending) is small
269 because the time is too short for global structural response to develop. During the loading phase,
270 explosion generates a stress wave propagating in the structure, which may cause concrete
271 crushing and spalling damage, as observed in the tests presented in this paper. After the action
272 of blast loads, the structure continues to deform because significant explosion energy has been
273 imparted into the structure and the global structural response modes and damage will be
274 induced.

275 The measured strains as shown in Figure 12 are associated with stress wave propagation in the
276 initial stage and followed by global structural responses with lower frequency contents. Stress
277 wave propagation results in rapid strain oscillations owing to wave reflection and refraction.
278 The measured strain associated to stress wave propagation also decays quickly with respect to
279 their distance to explosion. Taking NRC-1 as an example, the measured strain at gauge 1, which
280 is buried directly underneath explosion, is larger than those at gauge 2 and 3. Moreover, the
281 wave arrival time at gauge 1 is slightly earlier than that of gauge 2 and 3, which were placed
282 further away from the explosion. These observations confirm the measured strains are
283 associated with stress wave propagation.

284

285 The strain rates in all the tested slabs are derived from the recorded strain time histories. In
286 NRC-1, the explosive weight was 0.1 kg and the maximum strain rate reached 22000 s⁻¹. When

287 the explosive weight increased to 1.0 kg in NRC-2 slab, the maximum strain rate increased to
288 68000 s-1. For the UHPC slabs under 1 kg TNT contact explosion, strain rates around 50000
289 s-1 were noticed. The strain rate data reported in the present paper is ultra-high and not seen or
290 reported in previous studies. These ultra-high strain rate values were caused by shock wave
291 propagation in the specimen. As shown in Figure 12, in the global structure response stage, the
292 strain rate is substantially lower.

293

294 **3. Failure predictions using existing methods**

295 **3.1 Theoretical prediction methods**

296 Theoretical predictions on concrete spall damage is not straightforward because there are many
297 unknown parameters and uncertainties such as the influence of charge geometry on blast loads,
298 stress wave propagation and attenuation rate in concrete, wave dispersion effects, dynamic
299 compressive strength and tensile strength under high and varying strain rates. As a result, the
300 existing theoretical methods have to be used with some assumptions and simplifications [11,
301 12]. It was reported [27] that the theoretical methods do not necessarily give accurate
302 predictions to concrete damage under close-in blast loads.

303 **3.2 Empirical prediction methods**

304 It is commonly acknowledged that empirical methods which are primarily based on large
305 number of test trials are expensive to develop. Their application scopes are limited to situations
306 similar to the data upon which the empirical methods were based.

307 In the widely used design guideline UFC 3-340-02 [24], prediction of concrete spall under blast
308 loading condition is discussed and spall test results have been compiled and plotted. Threshold
309 spall and breach curves are plotted as approximate upper bounds to the spall and breach data

310 points, and these curves may be used in practical analysis and design to approximately predict
311 the concrete spall damage. However, it is noticed the configurations in all these tests are
312 different from the current study and thus the empirical damage curves are not applicable for
313 predicting the slab response in the present study.

314 After reviewing test data from 334 field blast tests, McVay [13] compiled the test data and
315 proposed empirical formulae to predict the local damage of concrete slabs subjected to bare
316 explosive charges. As shown in Figure 13, T is the slab thickness, R is the standoff distance in
317 unit of meter, and for contact explosion, R is taken as one-half of the outer diameter of the
318 cylindrical explosive charge, W is the charge weight, $T/W^{1/3}$ and $R/W^{1/3}$ are scaled slab
319 thickness and scaled standoff distance, respectively. In McVay's method, the unit used is kg
320 and m . Table 4 summarizes the corresponding parameters obtained from the current study.
321 After substituting these parameters into Figure 13, it is noted that the empirical evaluation can
322 give good prediction of spall damage of the two tested NRC slabs under contact explosion. For
323 UHPC slab 3 which has the same scaled slab thickness and scaled standoff distance as NRC-1,
324 empirical predictions derived by McVay underestimate its spall resistance capacity and give
325 inaccurate prediction. For UHPC slabs 4 and 7, they have the same scaled slab thickness and
326 scaled standoff distance as NRC-2, the observed spall damages, however, are substantially
327 smaller, and these are not reflected from the empirical predictions. For UHPC 5 and 6 with
328 different slab depths as compared with NRC-2, empirical methods give good predictions to the
329 slabs perforation. As indicated in Figure 13, although these testing data were obtained from
330 NRC slabs, they give good predictions of UHPC spall and breach damage. This is because the
331 boundary lines in the graph only give a very broad range of these damages, but not detailed
332 damage severities. As indicated in Table 3, although both the NRC and UHPC slabs could both
333 experience spall and perforation damage, the damaged area of UHPC slab is always smaller
334 than that of NRC slab because of the higher UHPC strength than NRC. To more accurately

335 quantify the damage severity, more studies, either blast testing or numerical simulations using
336 verified numerical models, are deemed necessary.

337

338 Based on McVay's formulae and their own tests results, Morishita et al. [28] proposed new
339 formulae to predict the contact explosion induced concrete slab damage as given below:

340 Limit of crater: $T/W^{1/3} > 3.6$ (1)

341 Limit of crater and spall: $2.0 \leq T/W^{1/3} \leq 3.6$ (2)

342 Limit of perforation: $T/W^{1/3} \leq 2.0$ (3)

343 The values of $T/W^{1/3}$ based on Morishita's method are given in Table 4 as well, the unit used
344 in Morishita's formulae given above is $cm/g^{1/3}$. Applying the above formulae to the present
345 study, it is again noticed that although the NRC slabs damage modes are well predicted, the
346 performance of UHPC slabs like UHPC-3 are underestimated.

347 These comparisons demonstrate that the existing empirical methods, which were derived based
348 on testing data on NRC slabs, can underestimate the performance of UHPC slab subjected to
349 contact explosions. It should also be noted that these empirical predictions do not consider the
350 influences of reinforcements, which certainly affect the spall damage of RC slabs. In future
351 study, numerical tool will be adopted to investigate the UHPC slabs under contact explosions.

352 The current test results will be used to calibrate the numerical model, and the verified numerical
353 model will be used to conduct extensive contact explosion simulations.

354 **4. Fragments distribution**

355 Safety concern is always related with accidental explosions. The injuries under blast loading
356 environment can be divided into five mechanistic types [29], in which secondary injuries
357 induced by fragments under blast environment are of particular concerns.

358 As well discussed in the previous studies, contact explosion on brittle material like concrete
359 can generate large number of fragments displacing from the material surface at high velocities
360 and these fragments are responsible for the human casualties and economic loss in those blast
361 scenarios. It is thus important to investigate the fragment velocity, launching distance and size
362 distribution for concrete material. Unfortunately, the current test data only allow examining the
363 fragment size distributions. Until now, although some work has been carried out identifying
364 the fragments distribution of normal strength concrete material, no discussion or effort had
365 been made to understand the size distribution of fragments from UHPC material under blast
366 loading.

367 In the current study, complete samples of fragments from both NRC slabs and UHPC slabs
368 were collected and sieved. Six sieves with size range from 0.6 mm to 15 mm were used. The
369 weights of fragments passing through each sieve had been measured as shown in Figure 14.

370

371 Fragment samples of NRC and UHPC passing through each sieve are shown in Figure 15. It is
372 observed that fragments from NRC slabs have relatively more regular shapes while the shapes
373 of fragments from UHPC slab are more irregular due to the existence of the micro fibre
374 reinforcement.

375 A typical comparison between UHPC-4 slab and NRC-2 slab is made and shown in Figure 16.
376 As depicted in the figure, under the same blast loading condition, NRC slab generates more
377 fragments than UHPC slab and the fragments weights passing through every sieve level are all
378 higher than UHPC slab.

379 Under impact or blast loading condition, size distribution of fragments from brittle materials
380 like rock and concrete is usually described by Weibull distribution which was suggested by
381 Grady and Kipp [30]. Weibull distribution is suitable for handling characteristics of the
382 cumulative distribution of fragment fractions. The cumulative density function is described by

383
$$P(<D) = 1 - \exp [-(D/D^*)^n] \quad (4)$$

384 where $P(<D)$ is the cumulative weight percentage of all fragments with diameters smaller than
385 D . The parameter D^* is defined as the scale parameter or characteristic diameter which is
386 referred to as the maximum mean diameter of the fragment, and n is a shape parameter which
387 is referred to as the Weibull modulus.

388 Figure 17 shows the standard size distribution of fragments from all the tested slabs except
389 UHPC-3 and UHPC-5. Blast load only generated a small crater in UHPC-3 and no perforation.
390 Therefore only very few fragments underneath the slab were collected as shown in Figure 7.
391 As shown in Figure 9, blast flame caused damage of the rug placed underneath the slab for
392 fragments collection. This made the collection of fragments from UHPC-5 difficult. Therefore
393 fragments from UHPC-3 and UHPC-5 are not included in the analyses here. It is obvious in
394 Figure 17 that the fragment size distributions from UHPC slabs differ from those from the two
395 NRC slabs, indicating Weibull distribution is not a representative distribution type of the
396 fragment sizes generated from UHPC slabs due to contact explosions.

397 Data from limited experimental observations suggested that the distribution parameter i.e. n in
398 Weibull distribution varies significantly. Direct impact experiments conducted by Costin and
399 Grady [31] showed n with a range between 2 and 3. O'keefe et al. [32] summarized fragment
400 size distributions from nuclear and chemical explosions, and a value of n between 0.4-0.55 was
401 noticed.

402 For the fragments generated from the contact explosion tests in the current study, as depicted
403 in Figure 18, Weibull distribution with modulus of 1.63 and 0.67 can well represent the size
404 distribution of fragments from NRC-1 slab and NRC-2 slab. Residual sum of squares (R^2 values)
405 are 0.976 and 0.95 for NRC-1 and NRC-2 slabs, respectively.

406

407 After careful examination, it is found that Log-normal distribution can well represent the size
408 distributions of fragments from UHPC slabs.

409 The cumulative distribution function is

$$410 P(< D) = \frac{1}{2} \left[1 + \operatorname{erf} \left(\frac{\ln x - \mu}{\sigma\sqrt{2}} \right) \right] = \frac{1}{2} \operatorname{erfc} \left(-\frac{\ln x - \mu}{\sigma\sqrt{2}} \right) = \phi \left(\frac{\ln x - \mu}{\sigma} \right) \quad (5)$$

411 where erf is an error function and erfc is the complementary error function, Φ is the cumulative
412 distribution function of the standard normal distribution. μ is the location parameter and σ is
413 the scale parameter.

414 As depicted in Figure 19, size distribution of fragments from UHPC slabs fits well the Log-
415 normal distribution. Location parameters and scale parameters are plotted for each fitting.
416 Residual sum of squares (R^2 values) are 0.89, 0.94 and 0.93 for UHPC-4, UHPC-6 and UHPC-
417 7 slabs, respectively.

418

419

420 **Conclusions**

421 Concrete spall and crush are important damage modes under blast loading condition, and these
422 phenomena become prominent when the explosives are detonated in close proximity to or in
423 contact with concrete structures. Concrete spall and crater cause severe loading capacity loss

424 and fragments generated with spallation can eject from concrete surface with high velocity
425 which will bring further threat to personnel and instruments shielded by the concrete structures.
426 In the present study, concrete slabs made with normal strength concrete material and ultra-high
427 performance concrete material are tested under contact explosions. Spallation and cratering are
428 observed and investigated quantitatively. UHPC slabs displayed significantly improved blast
429 resistance capacity than NRC slabs. Empirical methods developed based on large number of
430 tests are adopted to evaluate the performance of slabs in the current study and it is noted these
431 empirical methods can give good predictions on concrete spallation of NRC slabs but can
432 significantly underestimate the spall resistance of UHPC slabs. Size distributions of fragments
433 are investigated and it is noted that Weibull distribution can be used to represent the fragment
434 sizes from NRC slabs while fragments from UHPC slabs can be fitted to Log-normal
435 distributions.

436

437 **Acknowledgements**

438 The research presented in this paper jointly supported by the National Natural Science
439 Foundation of China under Grants 51278326 and 51238007, and the ARC Discovery Grant
440 DP140103025 is gratefully acknowledged.

441 **References**

- 442 [1] H.Y. Low, H. Hao, Reliability analysis of direct shear and flexural failure modes of RC
443 slabs under explosive loading, Engineering Structures, 24 (2002) 189-198.
444 [2] J. Li, H. Hao, Influence of brittle shear damage on accuracy of the two-step method in
445 prediction of structural response to blast loads, International Journal of Impact Engineering, 54
446 (2013) 217-231.

- 447 [3] T. Krauthammer, Shallow-buried RC box-type structures, Journal of Structural Engineering,
448 110 (1984) 637-651.
- 449 [4] J. Li, H. Hao, A Two-step Numerical Method for Efficient Analysis of Structural Response
450 to Blast Load, International Journal of Protective Structures, 2 (2011) 103-126.
- 451 [5] J. Dragos, C. Wu, Interaction between direct shear and flexural responses for blast loaded
452 one-way reinforced concrete slabs using a finite element model, Engineering Structures, 72
453 (2014) 193-202.
- 454 [6] B. Luccioni, R. Ambrosini, R. Danesi, Analysis of building collapse under blast loads,
455 Engineering structures, 26 (2004) 63-71.
- 456 [7] J. Li, H. Hao, Numerical study of structural progressive collapse using substructure
457 technique, Engineering Structures, 52 (2013) 101-113.
- 458 [8] Z.P. Bažant, M. Verdure, Mechanics of progressive collapse: Learning from World Trade
459 Center and building demolitions, Journal of Engineering Mechanics, 133 (2007) 308-319.
- 460 [9] G. Szuladziński, A. Szamboti, R. Johns, Some Misunderstandings Related to WTC
461 Collapse Analysis, International Journal of Protective Structures, 4 (2013) 117-126.
- 462 [10] J. Li, H. Hao, Numerical study of concrete spall damage to blast loads, International
463 Journal of Impact Engineering, 68 (2014) 41-55.
- 464 [11] C. Kot, R. Valentin, D. McLennan, P. Turula, Effects of air blast on power plant structures
465 and components, in, Argonne National Lab., IL (USA), 1978.
- 466 [12] C. Kot, Spalling of concrete walls under blast load, in: Structural mechanics in reactor
467 technology, 1977.
- 468 [13] M.K. McVay, Spall damage of concrete structures, in, DTIC Document, 1988.
- 469 [14] W. Wang, D. Zhang, F. Lu, S.-c. Wang, F. Tang, Experimental study and numerical
470 simulation of the damage mode of a square reinforced concrete slab under close-in explosion,
471 Engineering Failure Analysis, 27 (2013) 41-51.

- 472 [15] K.A. Marchand, B.T. Plenge, A.F.R.L.M.D. Lethality, V. Branch, S.R. Institute,
473 U.S.A.F.M. Command, Concrete Hard Target Spall and Breach Model, Air Force Research
474 Laboratory, Munitions Directorate, Lethality & Vulnerability Branch, 1998.
- 475 [16] E.B. Williamson, O. Bayrak, G.D. Williams, C.E. Davis, K.A. Marchand, A.E. McKay,
476 J.M. Kulicki, W. Wassem, Blast-Resistant Highway Bridges: Design and Detailing Guidelines,
477 in, 2010.
- 478 [17] K.-C. Wu, B. Li, K.-C. Tsai, The effects of explosive mass ratio on residual compressive
479 capacity of contact blast damaged composite columns, Journal of Constructional Steel
480 Research, 67 (2011) 602-612.
- 481 [18] K.-C. Wu, B. Li, K.-C. Tsai, Residual axial compression capacity of localized blast-
482 damaged RC columns, International Journal of Impact Engineering, 38 (2011) 29-40.
- 483 [19] B. Riisgaard, A. Gupta, P. Mendis, T. Ngo, Enhancing the performance under close-in
484 detonations with polymer reinforced CRC, Electronic Journal of Structural Engineering 6
485 (2006): 75-79.
- 486 [20] C. Wu, R. Nurwidayati, D.J. Oehlers, Fragmentation from spallation of RC slabs due to
487 airblast loads, International Journal of Impact Engineering, 36 (2009) 1371-1376.
- 488 [21] M. Ohtsu, F.A. Uddin, W. Tong, K. Murakami, Dynamics of spall failure in fiber
489 reinforced concrete due to blasting, Construction and Building Materials, 21 (2007) 511-518.
- 490 [22] K. Ohkubo, M. Beppu, T. Ohno, K. Satoh, Experimental study on the effectiveness of
491 fiber sheet reinforcement on the explosive-resistant performance of concrete plates,
492 International Journal of Impact Engineering, 35 (2008) 1702-1708.
- 493 [23] M. Foglar, M. Kovar, Conclusions from experimental testing of blast resistance of FRC
494 and RC bridge decks, International Journal of Impact Engineering, 59 (2013) 18-28.
- 495 [24] UFC, Structures to resist the effects of accidental explosions, in, Department of Defense,
496 Unified Facilities Criteria 3-340-02, Washington, DC.

- 497 [25] C. Wu, D.J. Oehlers, M. Rebentrost, J. Leach, A.S. Whittaker, Blast testing of ultra-high
498 performance fibre and FRP-retrofitted concrete slabs, *Engineering Structures*, 31 (2009) 2060-
499 2069.
- 500 [26] M. Beppu, T. Ohno, K. Ohkubo, B. Li, K. Satoh, Contact Explosion Resistance of
501 Concrete Plates Externally Strengthened with FRP Laminates, *International Journal of*
502 *Protective Structures*, 1 (2010) 257-270.
- 503 [27] J. Li, H. Hao, Numerical and Theoretical Study of Concrete Spall Damage under Blast
504 Loads, in: *Applied Mechanics and Materials*, Trans Tech Publ, 2014, pp. 774-779.
- 505 [28] M. Morishita, H. Tanaka, T. Ando, H. Hagiya, Effects of Concrete Strength and
506 Reinforcing Clear Distance on the Damage of Reinforced Concrete Slabs Subjected to Contact
507 Detonations, *Concrete Research and Technology*, 15 (2004) 89-98.
- 508 [29] S. Lord, R. Nunes-Vaz, A. Filinkov, G. Crane, Airport front-of-house vulnerabilities and
509 mitigation options, *Journal of Transportation Security*, 3 (2010) 149-177.
- 510 [30] D. Grady, M. Kipp, Dynamic rock fragmentation, *Fracture mechanics of rock*, 475 (1987).
- 511 [31] D.A. Shockley, D.R. Curran, L. Seaman, J.T. Rosenberg, C.F. Petersen, Fragmentation of
512 rock under dynamic loads, in: *International Journal of Rock Mechanics and Mining Sciences*
513 & Geomechanics Abstracts, Elsevier, 1974, pp. 303-317.
- 514 [32] J.D. O'Keefe, T.J. Ahrens, Impact and explosion crater ejecta, fragment size, and velocity,
515 *Icarus*, 62 (1985) 328-338.

516