

1 Sustainable Utilization of Lime Kiln Dust as Active Filler in Hot Mix Asphalt with 2 Moisture Damage Resistance

3
4 **Abstract:** The Australian flexible road pavement network is experiencing a considerable degree
5 of reeling and stripping damage in association with moisture. The next generation of hot mix
6 asphalt (HMA) mixtures in Australia needs to have excellent engineering properties as well as
7 higher resistance to moisture damage. Hydrated lime (HL) with a relatively high content of active
8 lime is used in HMA mixtures to improve engineering properties, and particularly to enhance the
9 resistance of HMA mixture to moisture. HL is currently considered a superior mineral filler to
10 crushed rock baghouse dust but it is commercially produced and relatively expensive. Lime kiln
11 dust (LKD) is an industrial by-product which has hydrated lime HMA filler-like properties with
12 similar fineness and a relatively high content of active lime. The lime components in LKD assists
13 in promoting resistance to the stripping common in siliceous acidic aggregates. This project aims
14 to determine an optimum proportion of LKD in an LKD-asphalt binder mixture, based on the
15 properties of viscoelasticity and aggregate adhesion. Dynamic shear rheometer testing and rolling
16 bottle tests were used to evaluate the properties of the LKD-asphalt binder mixtures with varying
17 LKD content. The test results indicated that a 50% LKD content in the LKD-HMA binder mixture
18 provided superior viscoelasticity properties., an acceptable adhesion of asphalt to aggregates was
19 also observed. Last but not the least, a ‘cradle to gate’ life cycle assessment was carried out to
20 capture the benefits of the use of LKD by-product. This showed that GHG emissions and embodied
21 energy demand could potentially be reduced by 18.5% and 2.4%, respectively if a 50% LKD
22 asphalt binder by mass mixture was used in the LKD-HMA mix..

23

24 *Keywords:* Lime Kiln Dust, Asphalt Concrete, Asphalt Binders, Dynamic Shear Rheometer,
25 Rolling Bottle Test, life cycle assessment

26

27 **1. Background and Introduction**

28 The construction industry consumes: 40% of natural materials, 40% of the total primary
29 energy, 15% of the world's fresh water resources, and generates 25% of all the wastes and 40 to
30 50% of green house gas (GHG) emissions [1]; the design team is thus charged to adopt an
31 environmentally responsible approach to their design solutions and construction materials'
32 specification choices. [1]. Among various major emitting industries, the construction sector offers
33 large abatement opportunities for emission reduction in the short-term due to its economic
34 importance and also opportunities for use of structurally-sound, low carbon intensive materials. In
35 the case of flexible pavements, asphalt (or bitumen), the binder used for the flexible pavement
36 surface material of a multi-layered road pavement system accounts for a significant portion of the
37 total life cycle GHG emission of the total pavement system. An asphalt concrete (AC) mixture (a
38 combination of an asphalt binder and aggregates) is considered a relatively thin surface layer of the
39 road pavement system. The use of asphalt during new road pavement construction and any
40 maintenance stages will result an increase in the overall life cycle GHG emissions of the flexible
41 pavement [1].

42 This paper highlights both the technical and environmental concerns associated with the use
43 of AC mixture in pavement. AC as a surface material can be referred to hot mix asphalt (HMA)
44 based on the construction process which requires high temperature (around 160°C) to create
45 workable asphalt when mixed with aggregate. Flexible (asphalt) pavements are vulnerable to
46 surface damage due to an increase in temperature, but more severe structural damage is caused by
47 an increase in water damage arising from wetter winters and more frequent intense rainfall events
48 [2]. Water can cause the loss of the adhesive bond between aggregates and an asphalt binder within

49 the AC surface layer and road pavements are damaged because the pavement strength and
50 durability is reduced [3]. This weakening, if severe enough, can result in stripping, which can lead
51 to various forms of HMA pavement distress, including rutting and fatigue cracking. For example,
52 McRobert and Foley [4] highlight a large degree of reeling and stripping damage that has recently
53 occurred in parts of the Great Eastern Highway, Western Australia. This issue has led to the
54 revision of current asphalt mix specifications to be more cognizant to this damage.

55 Mixtures of HMA have three main components: mineral aggregates; asphalt as a binder; and
56 air voids. In the HMA matrix, asphalt and mineral filler (mineral aggregates passing the No. 200
57 (less than 0.075 mm) sieve mesh were mixed to form a mastic coating. HMA can be considered as
58 a mixture of mastic-coated aggregates, in lieu of pure asphalt-coated aggregate [5]. Improved
59 mastic properties will result in better moisture damage resistance of HMA. In the early stage of
60 research on the mastic, Richardson [6] investigated several functions in the mastic and proposed
61 that not only just void-filling as originally thought, but also the physico-chemical phenomenon
62 existed in the mastic filler-asphalt system. From the late 1930s, the stiffening effect or
63 reinforcement mechanism of filler in the mastic was focused [7,8,]. Buttlar [9] provided a good
64 explanation of such reinforcement mechanisms. Reinforcement can be divided into three
65 categories: a) volume-filling reinforcement (stiffening resulted from the presence of solid (filler)
66 inclusions into a soft matrix (asphalt)), b) physico-chemical reinforcement (stiffening resulted from
67 interfacial effects between asphalt and filler particles, including absorption), and c) particle-
68 interaction reinforcement (stiffening resulted from interactions between filler particles and altered
69 asphalt). Based on knowledge of how filler plays a role in the performance of HMA by providing
70 reinforcement of the mastic in HMA, this study concentrates on using lime kiln dust (LKD) as an
71 active filler, instead of hydrated lime (HL), a commonly used active filler for improving moisture
72 damage resistance of HMA.

73 HL has a relatively high content of active lime in the form of calcium hydroxide ($\text{Ca}(\text{OH})_2$).
74 HL is generally used in HMA mixtures to improve engineering properties and particularly to
75 enhance the resistance of HMA mixtures to moisture [10]. HL is currently considered to be HMA
76 filler in accordance with ASTM C1097 and AASHTO M303, but it is commercially produced and
77 is an expensive material in HMA. Didier L., et al [11] performed a literature review of HL as an
78 active filler in HMA and noted that HL is an additive that increases HMA durability. The strong
79 interactions between both aggregates and an asphalt binder and a combination of four mechanisms,
80 two on the HMA aggregates and two on an asphalt binder are a reason behind the effectiveness of
81 HL in HMA [11]. HL modifies the surface properties of the HMA aggregate, allowing for the
82 development of surface composition and increased roughness favourable to asphalt binder
83 adhesion. HL also treats existing clay particles adhering to the aggregate surface, inhibiting their
84 detrimental effect on the mixture. HL reacts chemically with acids in the asphalt binder, which in
85 turn slows down age hardening kinetics and neutralizes the effect of the “bad” adhesion promoters
86 present inside an asphalt binder, enhancing the moisture resistance of HMA mixtures.

87 Like asphalt, HL is an energy intensive material to produce and will increase the overall GHG
88 emissions and costs, therefore, there is a need for consideration of an alternative materials. As a
89 result, the road construction industry has also incorporated a wide variety of by-products into HMA
90 road pavement in order to reduce CO_2 emissions. For the industrial by-products, Kahdhal [12]
91 stated that a range of by-products have potential for use in HMA for road construction purposes.
92 Previous studies [13-21] demonstrated that potential industrial by-products for HMA included fly
93 ash and bottom ash, from coal fired power plants. Fly ash can be used as a mineral filler in HMA
94 applications [22]. Generally, fly ash will typically meet specifications mineral fillers for gradation,
95 organic impurities, and plasticity and fulfil the main function of HMA mineral filler in increasing
96 the stiffness of the asphalt mortar matrix, improve the rutting resistance of pavements, and the
97 durability of the mix [20]. An et al. [23] demonstrated bottom ashes could also be utilized in HMA

98 by partial replacement of fine aggregate in the HMA aggregate matrix, but the bottom ash behaved
99 like lightweight aggregates which contain relatively high porosity; thus, it required higher amount
100 of asphalt binder in the HMA mixture. Since FA is mainly used as a replacement for cement in
101 concrete, and its supply is limited, other potential by-products to replace FA need to be explored.

102 Lime kiln dust (LKD) is another industrial by-product which has HMA filler-like properties
103 in both fineness and a relatively high content of active lime. LKD can be comprised of up to 30-
104 50% calcium oxide (CaO) and 30-50% calcium carbonate (CaCO₃) [24]. Therefore, the lime
105 components in LKD could assist in promoting resistance to the stripping that is most common in
106 siliceous acidic aggregates.

107 Previous studies [14,25] showed that LKD can be effectively used as active filler in HMA
108 mixtures and would offer higher sustainability performance in terms of cost saving and resource
109 conservation for future generations. (this is an opinion and unsubstantiated).

110 Jiupeng Z, et al [26] demonstrated that the component of calcium oxide (CaO) in the CaO-
111 asphalt system plays a major role in the superior rheological properties of the mastic. The
112 significant amount of CaO in HL and LKD could lead to greater stiffening of the mastic, resulting
113 in a better moisture damage resistance of HMA mixture with inclusion of HL or LKD.

114 In these aforementioned studies, LKD was considered as a very small portion of aggregates of
115 the whole HMA mixture. On the basis of high CaO content of LKD, the conclusion was drawn that
116 it could enhance the overall performance of HMA. However, the effect of LKD to the particular
117 moisture damage resistance of HMA through some fundamental investigations was not performed
118 in these studies. Therefore, this current research has applied dynamic shear rheometer and rolling
119 bottle test to determine the optimum amount of LKD for maximizing the moisture damage
120 resistance of HMA mixtures. These tests investigate the effects of LKD to the visco-elastic
121 properties of LKD-asphalt binder mixtures and the coating ability between binders and aggregates.

122 The estimation of optimum amount of LKD in HMA mixture would determine the environmental
123 and sustainability benefits associated with the replacement of HL with LKD in HMA mixture.

124 Studies have been performed to assess the sustainability of the use of industrial by-products
125 for infrastructure and chemical industries. The conversion of the NO_x (i.e. a generic term for the
126 nitrogen oxides) by-product to fertilizer was found to offer overall savings of 46%, 274% and 583%
127 reduction in GWP, acidification potential and eutrophication compared to conventional fertilizer
128 [27]. Nath et al [28] found that about 36%–43% of carbon footprint and 36%–38% of embodied
129 energy consumption can be avoided for different concrete covers due to replacement of 40% cement
130 with fly ash. The sustainability assessment of Biswas and Cooling [29] shows that the replacement
131 virgin sand and limestones with red sand (i.e. by-product of bauxite residue) for construction
132 purposes could potentially offer economic, social and environmental benefits. Line 136 to 146 is
133 completely irrelevant to this study.

134 The aim of this study is to assess and demonstrate the incorporation of LKD into HMA mixture
135 in order to increase the overall performance, concentrating on moisture damage resistance.
136 Furthermore, the life cycle GHG emission of HMA mixture using LKD as a main constituent
137 compared to HMA mixture with HL is considered.

138 To achieve the aim, the specific objectives are to:

- 139 • Determine an optimum for LKD filler in the mastic based on laboratory investigations.
- 140 • Perform an estimation of carbon footprint or life cycle GHG emissions and embodied
141 energy demand for the replacement of HL with LKD in HMA mixtures.

142 Firstly, this paper demonstrates an evaluation of an optimum ratio of LKD and asphalt binders
143 that show moisture damage resistance. Sophisticated test results from dynamic shear rheometer
144 (DSR) and rolling bottle test (RBT) were used as a basis to properly determine an optimum ratio
145 of LKD and asphalt binder mixtures. DSR tests were performed to detect rheology properties of
146 LKD and asphalt binder mixtures in a form of a master curve. RBT were also carried out to detect

147 a degree of affinity between aggregates and LKD and asphalt binder mixtures. Secondly, it was
148 estimated the amount of carbon footprint or life cycle GHG emissions and embodied energy
149 demand that could be avoided due to use of LKD as a replacement of HL in HMA mixtures. ISO
150 14040-44 guideline for life cycle assessment were applied to calculate these parameters in this
151 study.

152 The innovation in this work lies in the potential to rationally evaluate the possibility of using
153 a by-product into the road pavement construction in ways that fundamental technical approaches
154 were used in conjunction with the sustainability evaluation through the carbon footprint figure.
155 Within this study, a proper amount of LKD into HMA mixtures was determined based on the
156 combined results of DSR tests and RBT. This is to capture effects of LKD to the visco-elastic
157 properties of LKD-asphalt binder mixtures and the coating ability between binders and aggregates.
158 This determination is unique in the field of pavement engineering. Furthermore, the sustainability
159 evaluation was merged to the technical evaluation to create the definite evaluation of using LKD
160 in HMA mixtures.

161

162 2. Methods and materials

163 This section is divided into two parts. Firstly, an experimental procedure was developed to
164 determine an optimum ratio of LKD and asphalt binder that is moisture damage resistant. Secondly,
165 a life cycle assessment was conducted to determine the environmental implications of the use of
166 LKD as an asphalt filler. For quantifying the environmental implications of the use of LKD in
167 HMA mixtures, GHG emissions and embodied energy consumption indicators were estimated in
168 the LCA [1].

169

170 2.1 Experimental procedure

171 2.1.1 Materials

172 *Aggregate:* The aggregate used in this study was sourced from quarries around Perth to replicate
173 the physical aggregate properties used in asphalt pavement in the Perth metropolitan region.
174 Petrographic reports outlining the aggregate mineralogy shows that the aggregates sourced for this
175 study has a composition of 39% Quartz and 26% K-Feldspar.

176 *Asphalt binders:* The specified asphalt binder types of C170 and C320 were used in this study
177 following Standard Australia [30].

178 *Active fillers:* As active fillers of HMA, both HL and LKD were used in this study as reference
179 (normally used) and study materials, respectively.

180 HL is manufactured material obtained by treating quicklime with enough water to satisfy its
181 chemical affinity for water. Quicklime is manufactured through calcination of high carbonate
182 shells and at elevated temperatures. In this study, industrial hydrated lime was used as a reference
183 active filler as it was specified by Western Australia Mainroads (MRWA). HL has a typical bulk
184 density of 375 kg/m³ [31]. Cockburn Cement's MSDS states HL is composed of 80 % – 95 %
185 Calcium Hydroxide (Ca(OH)₂) with 95 % of particles passing through a 75-micron sieve [32].

186 LKD is the dust collected by the baghouse filters in a lime kiln during the calcination process.
187 LKD used in this study was sourced from Cockburn Cement Western Australia with their suggested
188 main composition and concentrations of CaO of 40%-60% and CaCO₃ of 40%-70% [33].

189

190 2.1.2 Tests

191 *DSR tests:*

192 For the sample preparation process of DSR tests, original binders of C170 and C320 were mixed
193 with HL and LKD using a high shear mixing machine. The binders were kept in 250 cc containers
194 and left in the oven at 160°C temperature (mixing temperature) overnight. A percentage of HL or
195 LKD by mass was directly added to a binder container almost immediately after it was taken from

196 the oven to assure a 160°C mixing temperature. Then, the mixing process was performed until the
197 HL or LKD-binder mixtures reached their (stable) consistency. The HL or LKD-binder mixtures
198 were produced batch by batch for the DSR test without storage to avoid the sedimentation which
199 would occur.

200
201 The DSR test is generally performed to observe the rheology properties of asphalt binders through
202 a series of dynamic shear modulus values and its corresponding phase angles in a range of test
203 temperatures between 4 and 88°C with a speed of rotation of 10 rad/sec [34]. The linear viscoelastic
204 properties of asphalt binders can be determined from the DSR test. Because asphalt binder is a
205 viscoelastic in nature, its phase angle normally falls in between 0° and 90°. A phase angle at the
206 value of 0° depicts the characteristic of an elastic solid and a phase angle at the value of 90°
207 represents that of a viscous liquid. In this study, based on the procedure of the test, the complex
208 shear modulus (G^*) and the phase angle (δ) were determined with varied test temperatures of 40,
209 50, 60, and 70°C and frequencies from 0.1 to 10 Hz (i.e., the speed of rotation) to form a data set
210 for constructing a master curve. The master curve is a single smooth curve which aligns multiple
211 temperatures of dynamic modulus values in frequency domains. This curve represents the dynamic
212 modulus values over an observed range of temperatures and frequencies. It is normally derived
213 from the complex modulus which consists of two parts; the real value part represents the elastic
214 stiffness, and the imaginary part represents the internal damping [35,36]. The dynamic modulus is
215 the absolute value of the complex modulus which is derived from a continuous sinusoidal (or
216 haversine load), without a rest period.


217
218 For the master curve generation, in this study, the original binders of C170 and C320 as well as the
219 HL or LKD-binder mixtures were characterised according to the master curve of the dynamic shear

220 modulus ($|G^*|$) with regard to varying temperatures and frequencies. The properties and the
 221 performance of asphalt as a HMA binder strongly depend on temperature and frequency (time).
 222 Consequently, the multiple lines of a set of dynamic moduli corresponding to an array of different
 223 temperatures in the frequency domains shown in Figure 1 can be observed. However, it would be
 224 much better to represent the performance of an asphalt binder in terms of a dynamic shear modulus
 225 ($|G^*|$) through a single smooth line, rather than multiple lines, in association with the Time-
 226 Temperature Superposition principle (TTS) [35]. TTS relies on a shift factor, $a(T)$ to be multiplied
 227 by frequencies, equation (1), to align multiple lines of different temperature correspondence into
 228 one temperature reference line, which is called the master curve. This study chose the Williams-
 229 Landel-Ferry (WLF) equation, equation (2), as a shift factor function.

230
$$\log f_r = \log f + \log[a(T)] \quad (1)$$

231
$$\log[a(T)] = \frac{-a_1(T-T_R)}{a_2+(T-T_R)} \quad (2)$$

232 Where f_r represents reduced frequency (Hz); f , frequency (Hz); $a(T)$, shift factor; T_R , reference
 233 temperature ($^{\circ}F$); T , temperature ($^{\circ}F$); a_1 , a_2 , fitting coefficient. Figure 1 demonstrates the master
 234 curve after shifting from various temperatures to be one smooth curve at a reference temperature
 235 on a frequency domain.




236

237 **Fig 1.** Dynamic modulus master curve.
238

239 *Rolling Bottle Test (RBT).* RBT used in this study was performed in accordance with the standard
240 of EN 12697-11:2012(E) (EN 12697-11 2012). It is the European Standard specifying procedures
241 for evaluating a degree of the affinity between aggregate and asphalt binders. This study used the
242 methods of EN12697 to determine the affinity between study aggregates and LKD-asphalt
243 mixtures and its influence on the susceptibility of the combination to moisture damages such as
244 stripping. In the method of RBT, the affinity can be represented with visual registration of the
245 degree of asphalt binder coverage on uncompacted asphalt binder-coated aggregate particles after
246 storage in water (EN 12697-11 2012). The study aggregate with a size range of 8-11 mm was
247 prepared at 510 g (for a batch of three test bottles) to reach a completely dry condition after placing
248 in a ventilated oven with a controlled temperature of 110°C for 24 hours. Then this dry aggregate
249 was mixed with a 3% binder content of study binders (C170, C320 and LKD-asphalt binder
250 mixtures) at a mixing temperature of 160°C. After mixing, a mixture was allowed to cool down to
251 a room temperature. The asphalt binder-aggregate mixture after cooling was then transferred to
252 the test bottles filled with approximately 50% by volume with distilled water with a temperature
253 of 5°C. The test bottles containing water and mixture were then installed on the bottle rolling
254 machine and the rolling process was commenced. At 6 and 24 hours of rolling, the aggregate
255 particles coated with an asphalt binder were taken out of the bottle to estimate the average degree
256 of binder coverage by visual observation. Visual observation was according to the reference
257 images for estimation of degree of binder coverage as shown in Figure 2. Pictures of RBT
258 conducted in this study are exhibited in Figure 3. It should be noted that to avoid personal bias
259 during visual inspections of RBT tests, the visual inspections were performed with at least three
260 inspectors to get agreement on the degree of particle coating for each test. A series of test result

261 values of these RBT tests were average values of a batch of three test bottles for a given ratio of
 262 study binders.



263

264

Fig 2. Graphical help of assessment of the degree of coating (Matin Istonbul 2012).



265

266

Fig 3. Pictures of RBT of this study.

267

268

2.2 Carbon footprint and embodied energy demand assessment

269 A life cycle assessment (LCA) approach has been applied to estimate carbon footprint and
 270 embodied energy consumption of the asphalt concrete mixtures following the guidelines of
 271 ISO14040-44 [37]. ISO14040 consists of four steps, namely: goal and scope, inventory analysis,
 272 impact assessment and interpretation.

273 The goal of this LCA is to evaluate the carbon footprint and embodied energy demand of the
 274 production and use of asphalt concrete mixtures. Six asphalt concrete mixes, as given in Table 1,
 275 were considered for LCA analysis: a control asphalt concrete mix with 100% hydrated lime, five
 276 asphalt concrete mixes with 10%, 20%, 30%, 40% and 50% LKD as a filler material.

277 The system boundary of this concrete LCA includes the mining to use stages of the product life
278 cycle. This consists of several stages including mining of raw material, manufacturing and
279 processing of construction materials, transportation of these materials to the asphalt concrete mix
280 plant and the production of asphalt concrete. The downstream stages including transportation of
281 asphalt concrete to pavement site, haulage of AC mixture in-place project, paving and rolling,
282 maintenance and end of life stages have been excluded as the experimental results of these stages
283 are not currently available. This is why this LCA is termed as a streamlined LCA following
284 Mohammed et al.[27].

285 The functional unit of this study is 1 m³ of asphalt concrete mix. A life cycle inventory analysis
286 was done to estimate energy and materials used during the aforementioned stages of asphalt
287 concrete mixes. Table 1 shows the LCI consisting of inputs, including coarse aggregates, fine
288 aggregates, hydrated lime, LKD, bitumen, transportation and electrical and thermal energy
289 consumption for six asphalt concrete mixes which were pre-requisites to carry out a life cycle
290 impact analysis.

291 Inputs of life-cycle inventory data in Table 1 were entered into SimaPro 8.2 LCA software
292 [38]; application which requires relevant materials to be linked to an Australian libraries or
293 emission databases to represent the Western Australia's (WA) situation. Where libraries did not
294 exist, new libraries were developed from similar LCA studies. The emission factor databases
295 include all upstream emissions and embodied energy demand of these inputs. The
296 Intergovernmental Panel on Climate Change -IPCC2007 method was used to calculate global
297 warming potential (GWP) of these mixes [39]. The cumulative energy demand method was used
298 to estimate their embodied energy demand.

299 Equation (3) presents the conversion of masses of different types of GHGs associated with
300 the production and use of material and energy inputs into GWP, which is a single carbon dioxide-
301 equivalent metric (CO₂ e-) [19].

302
$$GWP (CO_2 e -) = \sum_{i=1}^{i=N} \sum_{j=1}^{j=M} I_i EF_{ij} \times CF_j \quad (3)$$

303 where, I is the amount of an input

304 i : 1, 2, ..., N; type of inputs (e.g. aggregates, hydrated lime, transportation, electricity,
305 heating)

306 EF_{ij} : Emission factor = Amount of emission of GHG type 'j' per kg of input of type 'i'

307 CF_j : CF_1, CF_2, \dots, CF_M ; characterization factors of GHGs (e.g. 1 for CO_2 , 28 for CH_4 ,
308 265 for N_2O)

309 The inputs in the life-cycle inventory have been multiplied by the corresponding energy
310 demand values to find out the embodied energy demand of asphalt concrete mixes, which is
311 expressed as follows [37]:

312
$$EE_{total} = \sum_{i=1}^N I_i \times EE_i \quad (2)$$

313 where, EE_i is the embodied energy demand of an input i .

314

315
316**Table 1**
Life cycle inventory

Composition of asphalt concrete Mix	With HL	With LKD					Approximate distance between source to lab (km)	Location of material source
		10%	20%	30%	40%	50%		
Density (tonnes/m ³)	2.444	2.456	2.456	2.456	2.456	2.456	-	
Materials								
Course Aggregate (kg/m ³)	1,372.49	1,392.55	1,385.18	1,377.82	1,370.45	1,363.08	59.50	BGC Quarry, Great Southern Highway, Western Australia 6556, Australia
Fine Aggregate (kg/m ³)	915.00	928.37	923.46	918.54	913.63	908.72	59.50	-ditto-
HL (kg/m ³)	34.31	-	-	-	-	-	27.60	Cockburn Cement, Lot 242 Russell Road East, Munster WA 6166, Australia
LKD (kg/m ³)	-	12.28	24.56	36.84	49.12	61.40	27.60	-ditto-
Bitumen (kg/m ³)	122.20	122.80	122.80	122.80	122.80	122.80	18.20	Sami Bitumen Technologies, Cnr Birksgate & Port Beach Road, North Fremantle WA 6159, Australia
Transportation								
transportation of raw material to hot mix plant (tkm)*	139.28	140.67	140.28	139.89	139.49	139.10	-	
Energy								
Electricity consumption for preparation and mixing (kWh per tonne)	10	10	10	10	10	10	-	
Heat energy consumption for preparation and mixing (MJ per tonne)	300	300	300	300	300	300	-	

317

*tkm = tonne kilometer travelled by an input to asphalt plant

318
319

320 **3. Results and discussion**

321

322 *3.1 DSR*

323 In Figures 4 and 5, it can be seen that the dynamic shear modulus of the asphalt binder C170
324 and C320 mixed with all fillers is higher than the original asphalt binders and an increase in
325 modulus is proportional to the amount of LKD added (i.e., the more amount of filler is added, the
326 stiffer binder is obtained). Moreover, it is observed that the asphalt binders mixed with HL results
327 in the higher modulus than the one mixed with LKD at a replacement level of 30%. It was noted
328 that filler types affect the stiffness of an asphalt binder.

329 With consideration of a mixture of the asphalt binders C170 or C320 and 30%HL as a reference
330 material (i.e., 30%HL is a normally used HL content for a specified better performance asphalt
331 concrete for Western Australia), it could be seen that for both asphalt binders of C170 and C320,
332 LKD-asphalt binder mixtures of LKD contents of 40% and 50% exhibit the equal and higher
333 dynamic shear modulus values over a target range of reduced frequencies. Based on these DSR
334 results, promisingly, the LKD contents of 40% and 50% could be candidate LKD ratios for asphalt
335 concrete mixtures.

336

337 *3.2 RBT*


338 Figure 6 shows that the degree of binder coverage of the asphalt binder C170 mixed with all
339 fillers is higher than the original asphalt binders. An increase in degree of binder coverage is
340 proportional with the amount of LKD added (i.e., the more amount of filler added, the better affinity
341 and the lower moisture susceptibility of the binder). Affinity is improved, and the moisture

342 susceptibility could be reduced with an addition of more filler content. Moreover, it is observed
 343 that the asphalt binder mixed with HL results in the higher degree of binder coverage than the one
 344 mixed with the same amount of LKD (i.e.30%). For example, different degrees of binder coverage
 345 for the same proportion (i.e. 30%) of filler (i.e. LKD and HL), it could be demonstrated that types
 346 of filler affect the affinity and the moisture susceptibility of asphalt binders. In Figures 6 and 7, the
 347 similar findings can be seen for those of C320.

348


349 *3.3 Determine the optimum portion of LKD in an LKD-asphalt binder mixture*

350 According to the test results shown, adding more filler may improve the properties of asphalt
 351 binders (e.g., better affinity, and lower moisture susceptibility). As a result, the 50% LKD content
 352 was selected to be an optimum portion of LKD in the asphalt concrete mixture with better moisture
 353 damage resistance. This is because it can provide the best dynamic modulus and the best affinity
 354 with the study aggregate. Asphalt binders with much higher LKD content can cause highly viscous
 355 asphalt binder with less workability for construction purposes, a compromise between the service
 356 ability and the overall property of asphalt binders.50% of LKD added is the optimum portion of
 357 LKD in an LKD-asphalt binder mixture based on the study results.




358

359 **Fig 4.** Dynamic shear modulus of the original asphalt binder C170 and all the asphalt binder mixed with fillers.




360

361 **Fig 5.** Dynamic shear modulus of the original asphalt binder C320 and all the asphalt binder mixed with filler



362

363 **Fig 6.** Degree of bitumen coverage of the original asphalt binder C170 and all the asphalt binder mixed with fillers.




364

365 **Fig 7.** Degree of bitumen coverage of the original asphalt binder C320 and all the asphalt binder mixed with fillers.

366


367 *3.4 Environmental implications of the use of LKD in asphalt concrete mix*

368 A ‘cradle to gate’ life cycle assessment carried out to capture the environmental benefits of the
 369 use of LKD in HMA shows that GHG emissions and embodied energy demand could potentially
 370 be reduced by 18.5% and 2.4%, respectively if LKD, which is 50% of bitumen, is used in HMA
 371 mixtures (Figures 8 and 9). The increase in LKD in asphalt concrete (i.e. from 10% LKD to 50%
 372 LKD) slightly increases both GHG and embodied energy demand savings. This can be explained
 373 by the fact that the amount of energy- and carbon-intensive materials like coarse and fine aggregate
 374 in the asphalt concrete mix decreases with the increase in LKD (Table 1). This has other
 375 environmental benefits as the use of higher amount of LKD in HMA mixtures would reduce the
 376 amount of residue storage area of the cement factory (we do not mine land deposits for
 377 quicklime)(we are using old quarries for LKD disposal so no biodiversity loss)



378

379 **Fig 8.** GWP saving potential of asphalt concrete mixes using LKD



380

381 **Fig 9.** Embodied energy demand saving potential of asphalt concrete mixes using LKD

382

383 **4. Conclusions and recommendations**

384 This study aims to evaluate an optimum content of LKD in HMA based on the performance
 385 of LKD-asphalt binder mixtures through their rheology properties by the DSR tests and ability to
 386 coat an aggregate by the RBT tests. The test results indicate that a 50% LKD content by mass was
 387 an optimum ration between the mixtures of LKD and study asphalt binders of both C170 and
 388 C320. The LKD-asphalt binder mixtures provide good viscoelasticity properties based on a master
 389 curve series of the LKD-asphalt binder mixtures. Based on RBT test results, higher LKD contents
 390 in the LKD-asphalt binder mixtures resulted in better asphalt (bitumen) coverage for both study
 391 binders (C170 and C320). Furthermore, the use of a maximum amount of LKD (i.e. 50% of
 392 asphalt binder) in the HMA mixture could potentially reduce GHG emissions and embodied
 393 energy demand by 18.5% and 2.4%, respectively. Future research will consider the analysis of
 394 socio-economic implications of the use of this cement factory by-product as asphalt filler.

395 The addition of 50% LKD to normally used asphalt binders (e.g., C170 and C320) can
 396 definitely result in significantly higher viscosity. This would lead to less workability of
 397 construction (i.e., compaction). Proper mix design processes are strongly required to evaluate the

398 suitability of mixing 50% LKD-asphalt binder mixture with a given aggregate to form satisfying
399 asphalt concrete with LKD. All important properties of a target void ratio, a density, values of
400 stability and flow based on the Marshall method would need to be carefully determined to assure
401 that all asphalt concrete requirements of volumetric and strength properties as well as workability
402 still can be achieved with the addition of 50% LKD to a HMA mixture.

403 Finally, this study overcomes the uncertainty associated with the use of empirical results of
404 LKD use in HMA as active filler by conducting fundamental experiments that determines the
405 rational portion of LKD in HMA for maximizing the moisture damage resistance of HMA.

406

407 **5. Acknowledgements**

408 The authors wish to express their gratitude Cockburn Cement for the financial support of this
409 study, under the Cockburn Cement-Curtin University research project, conducted at the
410 Department of Civil Engineering, Curtin University. Thanks to Research Assistants Sarayoot
411 Kumlai and Krishna Lawania for their help in the experimental and life cycle assessment parts of
412 the research, respectively.

413

414 **References**

- 415 1. G.K. Ding, Life cycle assessment (LCA) of sustainable building materials: An overview, in
416 Pacheco-Torgal, F., Cabeza, L.F., Labrincha, J. & de Magalhaes, A. (eds), Eco-efficient
417 construction and building materials Life cycle assessment (LCA), eco-labelling and case
418 studies, Woodhead Publishing, Cambridge, UK, 2014:38-62.
- 419 2. Austroads, Impact of climate change on road performance. Austroads Incorporated, Sydney,
420 Rep. No. AP-R243, 2004

- 421 3. E.Y.Hajj, N. Morian, G.A El Tannoury, S.Manoharan, P.E. Sebaaly, Impact of lime
422 application method on ravelling and moisture sensitivity in HMA mixtures. International
423 Journal of Pavement Engineering, 12:02 (2011) 149-160.
- 424 4. J. McRobert, G. Foley, The impact of water logging and salinity on road assets; A western
425 Australian case study, Special report 57, ARRB transport research ltd., 1999.
- 426 5. Baoshan Huang , Xiang Shu & Xingwei Chen , Effects of mineral fillers on hot-mix asphalt
427 laboratory-measured properties, International Journal of Pavement Engineering, 8:1, 1-9,
428 (2007), DOI: 10.1080/10298430600819170)
- 429 6. Richardson, C., The Modern Asphalt Pavement, 1914, J. Wiley and Sons: New York
- 430 7. Traxler, R.N., The evaluation of mineral powders as fillers for asphalt. Proc. Assoc. Asphalt
431 Paving Technologists, 1937, 8, 60– 67.
- 432 8. Mitchell, J.G. and Lee, A.R., Evaluation of fillers for tar and other bituminous surfacings. J.
433 Soc. Chem. Industry, 1939, 58, 299.
- 434 9. Buttlar, W.G., Bozkurt, D., Al-Khateeb, G.G. and Waldhoff, A.S., Understanding asphalt
435 mastic behavior through micromechanics. Transportation Research Board 1681, pp. 157– 169,
436 1999 (Transportation Research Board: Washington, DC)
- 437 10. Lesueur, D., Hydrated lime: A proven additive for durable asphalt pavements – Critical
438 literature review. Brussels: European Lime Association (EuLA). (2010) Retrieved from
439 <http://www.eula.eu>
- 440 11. Didier Lesueur , Joëlle Petit & Hans-Josef Ritter (2013) The mechanisms of hydrated lime
441 modification of asphalt mixtures: a state-of-the-art review, Road Materials and Pavement
442 Design, 14:1, 1-16, DOI: 10.1080/14680629.2012.743669
- 443 12. S. K., Kahdhal, Waste Materials in Hot Mix Asphalt-An Overview , National Center of Asphalt
444 Technology, NCAT report No.92-6,1992.
- 445

- 446 13. W.K. Biswas, Carbon footprint and embodied energy consumption assessment of building
447 construction works in Western Australia, *International Journal of Sustainable Built*
448 *Environment* 3 (2) (2014) 179-186.
- 449 14. M. M. Miller, R. M. Callaghan, Lime kiln dust as a potential raw material in portland cement
450 manufacturing, U.S. Department of the Interior, U.S. Geological Survey, Open File Report
451 2004-1336, 2004.
- 452 15. N.Ali, J.S. Chan, S. Simms, R. Bushman, A.T. Bergan,. Mechanistic evaluation of fly ash
453 asphalt concrete mixtures. *Journal of Materials in Civil Engineering*, 8 (1) (1996) 19-25.
- 454 16. E.G. Bautista, J. Flickinger, R. Saha, I. Flores-Vivian, A.F. Faheem, K. Sobolev, Effect of Coal
455 Combustion Products on High Temperature Performance of Asphalt Mastics. *Journal of*
456 *Construction and Building Materials*, Vol. 94 (2015) 572-578.
- 457 17. E.V.Churchill, S.N.Amirkhanian, Coal ash utilization in asphalt concrete mixtures, *Journal of*
458 *Materials in Civil Engineering*, 11 (4) (1999). 295-301.
- 459 18. A. Covi, ASHphalt Paving: Better Performance Using Fly Ash – Amended Binders in Asphaltic
460 Concrete.” *Ash at Work*, 2013 Issue 1, American Coal Ash Association, (2013) 22-25.
- 461 19. A. Faheem, H. Bahia, Modeling of Asphalt Mastic in Terms of Filler-Bitumen Interaction. *The*
462 *International Journal of Road Materials and Pavements Design*, 11 – Special Issue, (2010) 281-
463 303.
- 464 20. K. Sobolev, I. Flores, N. M. Wasiuddin, The Use of Fly Ash as Filler in Asphalt Cement: Phase
465 I, Final Report, UWM-We Energies, 2011.
- 466 21. K. Ksaibati, J. Stephen, Utilization of bottom ash in asphalt mixes, Department of Civil &
467 Architectural Engineering, University of Wyoming; University of Wyoming; Laramie, WY,
468 1999.
- 469 22. American coal ash association, Fly Ash Fact for Highway Engineers, Technical Report
470 DTFH61-02-X-00044, Federal Highway Administration, Washington, DC, 2003.

- 471 23. J. An, J. Kim, B. K. Golestani, K.M.A.I. Tasneem, B.A. Muhit, B.H. Nam A.H. Behzadan,
472 Evaluating the Use of Waste-to-Energy Bottom Ash as Road Construction Materials”, Final
473 Report BDK 78-977-20, Office of Materials, State of Florida Department of Transportation,
474 Tallahassee, FL, 2014.
- 475 24. Cockburn Cement 2009a. Material Safety Data Sheet of Hydrated lime, Cockburn Cement,
476 Perth, Western Australia.
- 477 25. R.C. West, R.S. James, Evaluation of a Lime Kiln Dust as a Mineral Filler for Stone Mastic
478 Asphalt, Proceedings, 85th Annual Meeting of the Transportation Research Board, Washington
479 D.C., USA, 2005.
- 480 26. Jiupeng Zhang, Zepeng Fan, Dongliang Hu, Zhuang Hu, Jianzhong Pei & Weichuan Kong
481 (2016): Evaluation of asphalt–aggregate interaction based on the rheological properties,
482 International Journal of Pavement Engineering, DOI: 10.1080/10298436.2016.1199868.
- 483 27. F.Mohammed, W. Biswas, H. Yao, M. Tade, Identification of an Environmentally friendly
484 Symbiotic Process for the Reuse of Industrial Byproduct – an LCA Perspective, Journal of
485 Cleaner Production, 112 (2016): 3376-3387.
- 486 28. P. Nath, P. Sarker, and W.K. Biswas, Effect of fly ash on the service life, carbon footprint and
487 embodied energy of high strength concrete in the marine environment, Energy and Building,
488 158 (2017) 1694-1702.
- 489 29. W. K., Biswas, D. Cooling. Sustainability Assessment of Red Sand as a Substitute for Virgin
490 Sand and Crushed Limestone, Journal of Industrial Ecology 17(5) (2013) 756-762.
- 491 30. Standards Australia, Residual bitumen for pavements, AS 2008, Standards Australia, Sydney,
492 1997.
- 493 31. Western Australia Main Road (MRWA), Specification 511 - Materials for Bituminous
494 Treatments (2014).
- 495 32. Cockburn Cement 2006. General Specification, Cockburn Cement, Perth, Western Australia.

- 496 33. Cockburn Cement Material Safety Data Sheet of Lime Kiln Dust, Cockburn Cement, Perth,
497 Western Australia, 2009b.
- 498 34. American Society for Testing and Materials, Standard test method for determining the
499 rheological properties of asphalt binder using a dynamic shear rheometer, ASTM D7175-08,
500 West Conshohocken, PA, 2008.
- 501 35. Y.R. Kim, Modelling of Asphalt Concrete, 452, ASCE press, USA, 2009.
- 502 36. Y.H. Huang, Pavement Analysis and Design, 2nd edition, Prentice Hall, New Jersey, 2004.
- 503 37. ISO, ISO 14040:2006 - Environmental Management -- Life Cycle Assessment -- Principles
504 and Framework, International Organization for Standardization, Geneva, 2006.
- 505 38. Pré Consultants, SimaPro database. Pré Consultants, The Netherlands, 2016.
- 506 39. IPCC (Intergovernment Panel on Climate Change), Direct Global Warming Potentials, IPCC
507 Switzerland, 2007. https://www.ipcc.ch/publications_and_data/ar4/wg1/en/ch2s2-10-2.html
508